

Verdcol™ DPP Red 254 PTR

- Bright and highly saturated mid shade red
- High colour strength
- Good fastness to light and weather

Colour Index	Pigment Red 254
C.I. No.	56110
CAS No.	84632-65-5
REACH Pre-Registration No.	Available on Request


Physical Data	
Density[g/cm ³]	1.5~1.6
Specific Surface [m ² /g]	28~32
Oil Absorption[g/100g]	40~50

Application	
PVC	●
PE/PP	●
PS	●
ABS	○
PA	-
PC	-
PUR	●
PET/PBT	-
Rubber	●
● : recommended	
○ : limited suitability	
- : not recommended	

Fastness				
Light	Weather	Migration (In PVC)	Acid	Alkali
8	4~5	5	5	5




Full Shade



Tint 1:10 TiO₂

Heat Resistance (In HDPE)



For more details, please contact service@verdexinli.com