

Verdcol™ Scarlet 166

- Mid shade red
- Good fastness to light

Colour Index	Pigment Red 166
C.I. No.	20730
CAS No.	3905-19-9
REACH Pre-Registration No.	Available on Request

Physical Data


Density[g/cm ³]	1.4~1.5
Specific Surface [m ² /g]	25~30
Oil Absorption[g/100g]	50~55

Application


PVC	●
PE/PP	●
PS	●
ABS	○
PA	-
PC	○
PUR	○
PET/PBT	○
Rubber	○
●: recommended	
○: limited suitability	
-: not recommended	

Fastness

Light	Weather	Migration (In PVC)	Acid	Alkali
7~8	4-5	5	5	5




Full Shade



Tint 1:10 TiO₂

Heat Resistance (In HDPE)



For more details, please contact service@verdexinli.com