

Verdcol™ Red 144

- Mid shade red
- Good fastness

Colour Index	Pigment Red 144
C.I. No.	20735
CAS No.	5280-78-4
REACH Pre-Registration No.	Available on Request

Physical Data	
Density[g/cm ³]	1.4~1.5
Specific Surface [m ² /g]	30~35
Oil Absorption[g/100g]	60~65

Application	
PVC	●
PE/PP	●
PS	●
ABS	●
PA	-
PC	○
PUR	○
PET/PBT	○
Rubber	○
● : recommended	
○ : limited suitability	
- : not recommended	

Fastness				
Light	Weather	Migration (In PVC)	Acid	Alkali
7~8	4	5	5	5




Full Shade



Tint 1:10 TiO₂

Heat Resistance (In HDPE)



For more details, please contact service@verdexinli.com