

Verdcol™ Yellow 191 A

- Economical red shade yellow
- Excellent heat stability
- Recommended as replacement for diarylide and lead chromate

Colour Index	Pigment Yellow 191:1
C.I. No.	18795:1
CAS No.	154946-66-4
REACH Pre-Registration No.	Available on Request

Physical Data

Density[g/cm ³]	1.7~1.8
Specific Surface [m ² /g]	20~25
Oil Absorption[g/100g]	55~65

Application

PVC	●
LDPE	●
HDPE/PP	●
PS	●
ABS	●
PA	○
PC	○
PUR	●
PET/PBT	○
RUBBER	●
●: recommended	
○: limited suitability	
-: not recommended	

Fastness

Light	Weather	Migration (In PVC)	Acid	Alkali
8	4~5	5	5	5




Full Shade



Tint 1:10 TiO₂

Heat Resistance (In HDPE)



For more details, please contact service@verdexinli.com