

Verdcol™ Violet 19 B2

- Highly saturated violet
- High transparency and gloss
- High colour strength

Colour Index	Pigment Violet 19
C.I. No.	73900
CAS No.	1047-16-1
REACH Pre-Registration No.	Available on Request

Physical Data


Density[g/cm ³]	1.4-1.5
Specific Surface [m ² /g]	75-80
Oil Absorption[g/100g]	85-90
Heat Stability[°C]	200°C

Application

Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
8	4-5	5	5	4-5	4-5	5

For more details, please contact service@verdexinli.com