

## Verdcol™ DPP Red 254 PTR

- Bright and highly saturated mid shade red
- High colour strength
- Good fastness

Colour Index	Pigment Red 254
C.I. No.	56110
CAS No.	84632-65-5
REACH Pre-Registration No.	Available on Request

### Physical Data


Density[g/cm <sup>3</sup> ]	1.5-1.6
Specific Surface [m <sup>2</sup> /g]	28-32
Oil Absorption[g/100g]	40-50
Heat Stability[°C]	200°C

### Application

Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO<sub>2</sub>

### Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
8	5	5	5	5	5	5

For more details, please contact [service@verdexinli.com](mailto:service@verdexinli.com)