

## Verdcol™ Red 170 BN

- Mid shade red
- Semi-opacity

Colour Index	Pigment Red 170
C.I. No.	12475
CAS No.	2786-76-7
REACH Pre-Registration No.	Available on Request

### Physical Data


Density[g/cm <sup>3</sup> ]	1.4~1.5
Specific Surface [m <sup>2</sup> /g]	25~30
Oil Absorption[g/100g]	65~70
Heat Stability[°C]	160°C

### Application

Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
●: recommended	
○: limited suitability	
—: not recommended	



Full Shade



Tint 1:25 TiO<sub>2</sub>

### Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
6	3~4	5	5	4~5	4	4~5

For more details, please contact [service@verdexinli.com](mailto:service@verdexinli.com)