

Verdcol™ Scarlet 166

- Mid shade red
- Good fastness

Colour Index	Pigment Red 166
C.I. No.	20730
CAS No.	3905-19-9
REACH Pre-Registration No.	Available on Request

Physical Data

Density[g/cm ³]	1.4~1.5
Specific Surface [m ² /g]	25~30
Oil Absorption[g/100g]	50~55
Heat Stability[°C]	200°C

Application

Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
7~8	4~5	5	5	4~5	4~5	4

For more details, please contact service@verdexinli.com