

## Verdcol™ Red 144

- Mid shade red
- Good fastness

Colour Index	Pigment Red 144
C.I. No.	20735
CAS No.	5280-78-4
REACH Pre-Registration No.	Available on Request

### Physical Data

Density[g/cm <sup>3</sup> ]	1.4~1.5
Specific Surface [m <sup>2</sup> /g]	30~35
Oil Absorption[g/100g]	60~65
Heat Stability[°C]	200°C

### Application

Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO<sub>2</sub>

### Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
7~8	4	5	5	4	3~4	4

For more details, please contact [service@verdexinli.com](mailto:service@verdexinli.com)