

Verdcol™ Pink 122 GP

- Blue shade red
- High transparency and gloss
- Excellent fastness

Colour Index	Pigment Red 122
C.I. No.	73915
CAS No.	980-26-7
REACH Pre-Registration No.	Available on Request

Physical Data

Density[g/cm ³]	1.4-1.5
Specific Surface [m ² /g]	75-80
Oil Absorption[g/100g]	60-65
Heat Stability[°C]	200°C

Application

Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
7-8	4-5	5	5	4-5	4-5	5

For more details, please contact service@verdexinli.com