

Verdcol™ Red 112

- Medium shade red
- Relatively fastness
- Recommended for water based system

Colour Index	Pigment Red 112
C.I. No.	12370
CAS No.	6535-46-2
REACH Pre-Registration No.	Available on Request

Physical Data


Density[g/cm ³]	1.4~1.5
Specific Surface [m ² /g]	25~30
Oil Absorption[g/100g]	55~60
Heat Stability[°C]	200°C

Application

Automotive Coatings	—
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	—
Coil Coatings	—
Wood Coatings	—
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
6	3~4	5	5	2~3	2~3	2~3

For more details, please contact service@verdexinli.com