

Verdcol™ DPP Orange 73 R

- Highly saturated orange
- Good fastness


Colour Index	Pigment Orange 73
C.I. No.	561170
CAS No.	84632-59-7
REACH Pre-Registration No.	Available on Request

Physical Data

Density[g/cm ³]	1.3~1.4
Specific Surface [m ² /g]	20~25
Oil Absorption[g/100g]	48~51
Heat Stability[°C]	200°C

Application

Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
8	5	5	5	5	5	5

For more details, please contact service@verdexinli.com