

Verdcol™ BML Orange 64

- Brilliant mid shade orange
- Excellent heat resistance

Colour Index	Pigment Orange 64
C.I. No.	12760
CAS No.	72102-84-2
REACH Pre-Registration No.	Available on Request

Physical Data

Density[g/cm ³]	1.5~1.6
Specific Surface [m ² /g]	25~30
Oil Absorption[g/100g]	60~65
Heat Stability[°C]	200°C

Application

Automotive Coatings	—
Industrial Coatings	●
Decorative Coatings	○
Powder Coatings	●
Coil Coatings	●
Wood Coatings	○
●: recommended	
○: limited suitability	
—: not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
7~8	3~4	5	5	5	5	5

For more details, please contact service@verdexinli.com