

Verdcol™ Orange 43

- Pure shade orange
- High colour strength
- Good fastness

Colour Index	Pigment Orange 43
C.I. No.	71105
CAS No.	4424-06-0
REACH Pre-Registration No.	Available on Request

Physical Data

Density[g/cm ³]	1.5~1.6
Specific Surface [m ² /g]	35~40
Oil Absorption[g/100g]	80~85
Heat Stability[°C]	200°C

Application

Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	○
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
7~8	3-4	5	5	4-5	4-5	4-5

For more details, please contact service@verdexinli.com