

Verdcol™ Yellow 74 TR

- Green shade yellow
- Good transparency
- Good fastness

| | |
|-----------------------------------|----------------------|
| Colour Index | Pigment Yellow 74 |
| C.I. No. | 11741 |
| CAS No. | 6358-31-2 |
| REACH Pre-Registration No. | Available on Request |

Physical Data

| | |
|--------------------------------------|---------|
| Density[g/cm ³] | 1.3~1.5 |
| Specific Surface [m ² /g] | 45~50 |
| Oil Absorption[g/100g] | 40~45 |
| Heat Stability[°C] | 140°C |

Application

| | |
|-------------------------|---|
| Automotive Coatings | - |
| Industrial Coatings | ● |
| Decorative Coatings | ● |
| Powder Coatings | - |
| Coil Coatings | - |
| Wood Coatings | ● |
| ● : recommended | |
| ○ : limited suitability | |
| — : not recommended | |



Full Shade



Tint 1:25 TiO₂

Fastness

| Light | Weather | Acid | Alkali | BAC | MEK | Xylene |
|-------|---------|------|--------|-----|-----|--------|
| 6 | 3~4 | 5 | 5 | 3 | 3 | 2~3 |

For more details, please contact service@verdexinli.com