

Verdcol™ Yellow 74 SO

- Green shade yellow
- High opacity
- Good fastness

Colour Index	Pigment Yellow 74
C.I. No.	11741
CAS No.	6358-31-2
REACH Pre-Registration No.	Available on Request

Physical Data


Density[g/cm ³]	1.3~1.5
Specific Surface [m ² /g]	15~20
Oil Absorption[g/100g]	40~45
Heat Stability[°C]	140°C

Application

Automotive Coatings	-
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	-
Coil Coatings	-
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
6	4	5	5	3	3	2~3

For more details, please contact service@verdexinli.com