

## Verdcol™ BML Yellow 154

- Medium shade yellow
- Good opacity
- Recommended for water based system

<b>Colour Index</b>	Pigment Yellow 154
<b>C.I. No.</b>	11781
<b>CAS No.</b>	68134-22-5
<b>REACH Pre-Registration No.</b>	Available on Request

### Physical Data

Density[g/cm <sup>3</sup> ]	1.5~1.6
Specific Surface [m <sup>2</sup> /g]	12~19
Oil Absorption[g/100g]	55~60
Heat Stability[°C]	160°C

### Application

Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	○
Coil Coatings	-
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO<sub>2</sub>

### Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
8	5	5	5	4-5	3-4	5

For more details, please contact [service@verdexinli.com](mailto:service@verdexinli.com)