

Verdcol™ BML Yellow 151 GH

- Exceptional green shade yellow
- Good colour strength
- Relatively good opacity

Colour Index	Pigment Yellow 151
C.I. No.	13980
CAS No.	31837-42-0
REACH Pre-Registration No.	Available on Request

Physical Data


Density[g/cm ³]	1.5~1.6
Specific Surface [m ² /g]	20~23
Oil Absorption[g/100g]	45~50
Heat Stability[°C]	200°C



Full Shade

Application

Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Tint 1:25 TiO₂

Fastness

Light	Weather	Acid	Alkali	BAC	MEK	Xylene
8	4-5	5	3	4-5	4-5	4-5

For more details, please contact service@verdexinli.com